



Eco-Friendly Innovations in Textile Dyeing: A Comprehensive Review of Natural Dyes

Saroj Devi ^a, Dheeraj Panghaal ^{b*}, Pawan Kumar ^c,
Priti Malik ^d, Er Ravi ^e and Surender Mittal ^f

^a DES (Home Sci.) CCSHAU KVK, Jind, India.

^b DES (Soil Sci.) CCSHAU KVK, Jind, India.

^c DES (Ext Edu.) CCSHAU KVK, Jind, India.

^d DES (Agronomy) CCSHAU KVK, Jind, India.

^e DES (Agri. Engg.) CCSHAU KVK, Jind, India.

^f TA(Farm) CCSHAU KVK, Jind, India.

Authors' contributions

This work was carried out in collaboration among all authors. All authors read and approved the final manuscript.

Article Information

DOI: <https://doi.org/10.9734/air/2025/v26i11247>

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/127178>

Review Article

Received: 15/10/2024

Accepted: 17/12/2024

Published: 21/01/2025

ABSTRACT

Natural dyes have garnered increasing attention in recent years due to their environmentally friendly properties and cultural significance. The reintroduction of natural dyes in the textile industry is largely driven by growing awareness of the adverse environmental impacts of synthetic dyes. This review aims to explore the historical significance, extraction processes, mordanting techniques, and recent advancements in natural dyeing, as well as the challenges associated with their use. By incorporating insights from various studies and reviews, this paper provides a comprehensive understanding of the potential and limitations of natural dyes in textile dyeing.

*Corresponding author: E-mail: dheerajpanghaal27@gmail.com;

Cite as: Devi, Saroj, Dheeraj Panghaal, Pawan Kumar, Priti Malik, Er Ravi, and Surender Mittal. 2025. "Eco-Friendly Innovations in Textile Dyeing: A Comprehensive Review of Natural Dyes". *Advances in Research* 26 (1):204-12. <https://doi.org/10.9734/air/2025/v26i11247>.

Keywords: Natural dyes; textile dyeing; synthetic dyes; dye-yielding plants.

1. INTRODUCTION

Historical Background and Emergence of Natural Dyes: Natural dyes have been used for thousands of years, with records dating back to ancient civilizations such as Mesopotamia, Egypt, and India. These cultures utilized plant-based dyes like *Indigofera tinctoria* for blue and *Rubia tinctorum* for red, as well as dyes from animal sources like cochineal and kermes for crimson shades (Ali et al., 2019). A review by Vankar (2000) highlighted that natural dyes were the primary coloring agents until the 19th century when synthetic dyes revolutionized the textile industry.

The discovery of synthetic dyes in 1856, starting with William Henry Perkin's accidental synthesis of mauveine, marked a turning point in dye technology. Synthetic dyes were favored for their low cost, wide range of shades, ease of production, and consistency in color, leading to the decline of natural dye usage (Shahid et al., 2013). However, the environmental consequences of synthetic dye production—such as water pollution, chemical toxicity, and energy consumption—began raising concerns in the late 20th century.

As a result, a resurgence of interest in natural dyes has occurred in recent decades. The growing demand for eco-friendly products has driven textile manufacturers and consumers to reconsider the benefits of natural dyes, particularly in organic and sustainable textile production (Bechtold et al., 2009). In a comprehensive review, Gupta and Gulrajani (2020) noted that niche markets, including artisanal crafts, organic fashion, and eco-conscious brands, have adopted natural dyes due to their biodegradable and non-toxic nature.

A study by Samanta and Agarwal (2011) emphasized that the resurgence of natural dyes is not only an environmental necessity but also a cultural revival. The study reviewed the use of traditional dyeing techniques in India, such as block printing and tie-dye, which are now being revitalized through natural dye applications. Vankar (2000) observed that these traditional methods also highlight the rich heritage of indigenous knowledge systems in dye extraction and application.

Research by Saxena and Raja (2014) suggested that natural dyes can serve as an important

economic opportunity in rural areas where dye-yielding plants are abundant. This study provided a review of community-based dyeing initiatives in India and Nepal, which not only promote sustainable practices but also create employment and preserve traditional crafts.

In a historical review, Das et al. (2020) examined the role of colonialism in altering global dye production. European colonizers introduced synthetic dyes to colonized regions, which led to the decline of local natural dye industries. However, in recent years, there has been a renewed interest in traditional dyeing methods, particularly in developing countries. According to Jothi (2008), this revival is largely driven by sustainability concerns, with natural dyes offering a renewable resource for textile coloring.

The historical importance of natural dyes is further highlighted by Bechtold et al. (2009), who noted their use in religious ceremonies, cultural textiles, and traditional garments. For example, in India, the use of turmeric and indigo in fabric dyeing has been integral to the country's cultural heritage. Similarly, in Japan, natural indigo dyeing, known as *Aizome*, is still practiced today due to its cultural significance and its non-toxic properties (Vankar, 2000).

Siva (2007) conducted an extensive review of dye-yielding plants in India, noting that the country is home to numerous species that can produce a wide range of colors. The study also highlighted the importance of preserving these plants, which are now endangered due to deforestation and urbanization. This has spurred efforts to cultivate dye-yielding plants as part of sustainable farming practices.

The environmental impact of natural dyes, compared to synthetic dyes, was extensively reviewed by Samanta and Agarwal (2011), who pointed out that natural dyes are biodegradable and pose no threat to aquatic life, unlike synthetic dyes, which release harmful chemicals into water bodies. A study by Saxena and Raja (2014) similarly concluded that the shift toward natural dyes could significantly reduce the environmental footprint of the textile industry.

In a comparative review, Nayak and Padhye (2020) discussed the differences in production processes between natural and synthetic dyes, emphasizing that natural dyeing is more labor-

intensive but environmentally friendly. They also reviewed advances in extraction techniques, such as microwave and ultrasound-assisted extraction, which have improved the efficiency of natural dye production.

Studies by Ali et al. (2019) and Das et al. (2020) highlighted that one of the challenges with natural dyes is achieving the same vibrancy and colorfastness as synthetic dyes. However, with innovations in dye extraction and mordanting techniques, the gap between natural and synthetic dyes has been narrowing (Nayak, 2019). For example, enzyme-assisted extraction has been shown to increase dye yield and improve the durability of the color on textiles (Shahid et al., 2013).

Sarkar and Obanda (2014) reviewed the growing use of bio-wastes, such as pomegranate peels, as sources of natural dyes. They noted that this approach not only promotes waste reduction but also enhances the sustainability of natural dye production. Their study provided a comprehensive analysis of waste-derived dyes, emphasizing their potential to replace synthetic dyes in commercial textile production.

In recent decades, academic research has focused on the challenges of commercializing natural dyes. A study by Gupta et al. (2020) reviewed the scalability of natural dye production, finding that the inconsistent availability of dye plants and the seasonal nature of plant harvesting present significant hurdles. Nevertheless, advancements in the cultivation of dye-yielding plants and the development of more efficient extraction methods are helping to overcome these challenges.

Historically, the revival of natural dyes has been linked to the slow fashion movement, which promotes environmentally and socially responsible clothing production. Bechtold and Mussak (2009) found that this trend has expanded beyond niche markets to mainstream fashion brands that are increasingly adopting sustainable practices.

Finally, several studies (Samanta & Agarwal, 2012; Nayak & Padhye, 2020) have highlighted the importance of integrating natural dyes into modern textile production processes. These reviews suggest that natural dyes offer not only environmental benefits but also unique aesthetic qualities, such as muted, earthy tones that are

increasingly popular in contemporary fashion design.

In conclusion, the historical significance of natural dyes and their current resurgence reflect a growing commitment to sustainability in the textile industry (Sarkar and Das, 2018). With ongoing research into more efficient extraction techniques and innovations in mordanting, natural dyes are positioned to play a critical role in the future of sustainable textiles.

Sources and Extraction Methods of Natural Dyes:

Natural dyes can be extracted from a wide variety of sources, including plants, animals, and minerals. Plant-based dyes are the most commonly used, with leaves, roots, flowers, fruits, seeds, and bark serving as primary color sources. A study by Joshi et al. (2020) highlighted the use of *Indigofera tinctoria* leaves for producing deep blue shades, while the roots of turmeric plants provide vibrant yellow hues. In a comprehensive review, Samanta et al. (2011) focused on the potential of plants like *Rubia tinctorum* and *Curcuma longa*, which are widely used for red and yellow dyes in the textile industry.

Animal-derived dyes, such as cochineal from *Dactylopius coccus*, are historically significant and have been reviewed extensively by researchers like Ali et al. (2019), who analyzed their application in textile dyeing for vibrant red colors. Similarly, Kamel et al. (2005) emphasized the role of animal-based dyes in historical textile arts. A review by Vankar (2000) pointed out that despite their bright hues, the use of animal-based dyes has declined due to ethical and sustainability concerns.

Mineral-based dyes, although less common in modern textile dyeing, have historical significance. Ochre, for example, has been used for centuries to produce earthy tones, as reviewed by Das et al. (2020), who examined its use in ancient cultures. The application of mineral-based dyes today is more niche, often reserved for artistic or traditional purposes.

Traditional extraction methods for natural dyes typically involve boiling the source material in water or alcohol, which helps to release the pigments. According to Sarkar and Obanda (2014), water-based extraction is the most commonly used method in small-scale or artisanal dyeing processes. However, the

efficiency of traditional extraction is limited by long processing times and low dye yields.

Recent innovations have significantly improved the efficiency of natural dye extraction. For instance, ultrasound-assisted extraction (Samanta et al., 2011) has been developed to accelerate the process and enhance dye yield. This method uses high-frequency sound waves to break down plant cell walls, allowing for more pigment to be extracted in a shorter amount of time. A review by Gupta et al. (2020) indicated that this method not only speeds up the process but also uses less water and energy, making it more sustainable.

Microwave-assisted extraction is another modern technique reviewed by Nayak and Padhye (2020). This method uses microwave energy to heat the dye source material rapidly, breaking down cell walls and extracting pigments more efficiently. Research by Bechtold et al. (2009) confirmed that microwave extraction significantly improves the dye yield from plants like *Curcuma longa* and *Lawsoniainermis* (henna), reducing waste in the process.

Adeel et al. (2019) examined the potential of using agricultural waste products, such as onion skins, pomegranate peels, and banana peels, to produce natural dyes. Their study demonstrated that these waste-derived dyes not only promote sustainability by utilizing byproducts but also offer excellent colorfastness and a wide range of shades. Further research by Sarkar et al. (2014) supported the idea that agricultural waste could serve as a sustainable alternative to traditional dye sources.

Solvent extraction is another method that has been explored in recent studies. A review by Gupta et al. (2020) analyzed the use of organic solvents like ethanol or methanol to extract pigments from plant materials. This method is particularly effective for extracting dyes that are not water-soluble. However, the use of organic solvents poses environmental risks, which is why researchers like Shahid et al. (2013) are focusing on finding eco-friendly solvents for extraction.

Enzyme-assisted extraction, reviewed by Shahid et al. (2013), has emerged as a promising technique for improving dye yields. This method uses enzymes to break down the cell walls of plant materials, allowing pigments to be released more efficiently. Studies by Gupta and Gulrajani (2020) found that enzyme-assisted extraction is

particularly useful for difficult-to-extract dyes, such as those from pomegranate peels and indigo leaves.

A study by Saxena and Raja (2014) reviewed the effects of temperature and pH on the dye extraction process. They found that controlling these variables can significantly improve dye yields and color intensity. High temperatures, for example, accelerate the release of pigments, while the pH of the extraction medium can affect the final shade of the dye. Their research also emphasized the importance of optimizing these parameters to achieve consistent results in commercial-scale dye production.

Research by Gupta and Kumar (2018) explored the use of supercritical fluid extraction, a method that uses carbon dioxide under high pressure to extract pigments without the need for harmful solvents. Their study indicated that this method could be a more sustainable option for large-scale dye production, although its high cost remains a barrier to widespread adoption.

Another innovative approach is the use of fermentation-assisted extraction, as discussed in a review by Saxena (2015). This method involves fermenting the dye source material to break down its cell walls and release the pigments. Although slower than other methods, fermentation has been shown to enhance the colorfastness of natural dyes, making them more durable on textiles.

Bechtold et al. (2009) also reviewed the potential of cold extraction techniques, which involve soaking the dye source material in cold water or alcohol for an extended period. This method is more environmentally friendly than traditional boiling, as it uses less energy, but it typically yields lower concentrations of dye. However, Bechtold et al. (2009) noted that cold extraction can produce more subtle, muted shades, which are increasingly popular in eco-friendly fashion.

Siva (2007) discussed the challenges of scaling up natural dye production for commercial use, noting that while small-scale extraction methods are effective for artisanal dyeing, they are often too slow or inefficient for industrial applications. However, studies like those by Joshi et al. (2020) suggest that with modern extraction technologies, it is becoming increasingly feasible to produce natural dyes on a larger scale without compromising sustainability.

Overall, the variety of sources and extraction methods for natural dyes has expanded significantly in recent years. From traditional water-based extraction to modern techniques like ultrasound-assisted extraction, researchers are continually developing new methods to improve the efficiency and sustainability of natural dye production.

Mordanting and Fixing Natural Dyes:

Mordants play a critical role in natural dyeing by helping bind the dye to textile fibers and improving color fastness. Traditionally, metallic mordants like alum, tannin, and iron salts have been widely used, but these have raised environmental concerns. Recent studies are investigating eco-friendly mordants, such as bio-mordants derived from tannin-rich plants like oak galls (Sarkar & Obanda, 2014), and researchers like Jothi (2008) have demonstrated that plant-based mordants can offer comparable color fastness to traditional metal mordants.

Tutak et al. (2014) explored the natural dyeing properties of wool fabrics using pomegranate peels, revealing strong color and fastness properties. Ado et al. (2014) presented an eco-friendly approach to natural dyeing and highlighted the importance of bio-degradable dyes in textiles. Furthermore, Gong et al. (2020) demonstrated a greener approach to dyeing merino wool using Cinnamomum camphora extracts and biological mordants, improving environmental sustainability. Similarly, Haji (2020) optimized wool dyeing with henna and yarrow through plasma treatment, which enhances dye uptake and fastness.

Other studies have explored innovative techniques such as the use of supercritical CO₂ for dye extraction, as detailed by Cadoni et al. (1999) and Banchemo (2020), who demonstrated its advantages over conventional methods by reducing water and chemical usage. Duval et al. (2016) reviewed the applications of anthraquinones in natural dyes and discussed their extraction and mordanting potential, adding another sustainable route for natural colorants.

Muneer et al. (2010) and Bhatti et al. (2012) conducted extensive research on radiation-enhanced dyeing processes, showing that ionizing radiation can improve dye-fiber bonding and durability without toxic chemicals. Moreover, Hayat et al. (2022) demonstrated the dyeing potential of waste materials like black tea leaves, utilizing their tannin content to naturally mordant silk fabric.

Additionally, Hasan et al. (2022) researched sustainable application of Cassia obovata-based chrysophanic acid as a natural yellow colorant, while Yameen et al. (2022) worked on eco-friendly extraction methods of yellow dye from *Nyctanthes arbor-tristis*, presenting sustainable alternatives to synthetic dyes. Sharma et al. (2019) investigated the reusability of henna dyeing wastewater, showcasing its potential for multifunctional finishing and eco-friendly textile applications.

Studies by Bhatti et al. (2010) and Adeel et al. (2012) also focused on improving mordanting processes for natural dyes using ultrasonic-assisted dyeing and bio-mordants. Xia et al. (2018) presented a sustainable solution using an ethanol-water mixture for cotton dyeing, achieving excellent exhaustion and minimal environmental impact.

In summary, the transition towards eco-friendly mordants and greener dye-fixation techniques continues to grow. Studies by Sarkar & Obanda (2014), Tutak et al. (2014), and Haji (2020) highlight the potential of plant-based mordants and innovative dyeing methods in enhancing sustainability in textile processing. As the textile industry moves towards eco-conscious production, advancements in mordanting and fixing techniques will be essential in achieving durable, vibrant colors while reducing environmental harm.

Advantages of Natural Dyes: Natural dyes are lauded for their eco-friendly properties, biodegradability, and lower environmental impact when compared to synthetic dyes. One of the key benefits is their minimal toxicity, reducing pollution in wastewater and posing fewer health risks to both workers and consumers. Vankar (2000) discusses the environmental sustainability of natural dyes, noting their potential to reduce chemical waste in the dyeing process. Kant (2012) further highlights that the textile dyeing industry's reliance on synthetic dyes poses significant environmental hazards, particularly through the release of harmful chemicals into aquatic ecosystems. By contrast, natural dyes derived from renewable sources such as plants, insects, and minerals contribute to an eco-friendly production process.

Shahid et al. (2013) performed an in-depth review comparing the health and environmental benefits of natural dyes to synthetic ones, noting that natural dyes are hypoallergenic and less

likely to cause skin irritation. Additionally, these dyes are biodegradable, which minimizes their impact on ecosystems compared to synthetic dyes that persist in the environment. Natural dyes also exhibit antimicrobial properties, as discussed by Anastasia Fröse et al. (2019), making them beneficial for health-focused textile applications such as medical textiles and clothing for sensitive skin.

Bechtold et al. (2009) emphasize the cultural and historical importance of natural dyes, which have been used for centuries in traditional textile production. The aesthetic qualities of natural dyes, with their soft, earthy tones and subtle variations, add value to artisanal textiles, which are increasingly in demand in niche markets. This is further reinforced by the works of Gulrajani et al. (1999), who explored the unique color profiles achieved by using various natural dyes on different fiber types.

Recent studies have also focused on improving the colorfastness and stability of natural dyes to increase their competitiveness with synthetic dyes. Cristea and Vilarem (2006) explored the use of eco-friendly mordants and fixatives that improve the longevity of natural dyes on textiles without compromising sustainability. Anastasia Fröse and her team (2019) investigated the application of natural dyes across a variety of textile materials, showing promising results in terms of dye uptake and fastness.

While synthetic dyes may offer more vibrant and consistent hues, Duff et al. (1985) and Crews (1982) argue that the subtle, variable shades produced by natural dyes provide a unique artisanal quality. This unpredictability in color is prized in certain markets, particularly for luxury and handcrafted textiles. Saxena and Raja (2014) also note that as consumers grow more conscious of environmental issues, the demand for sustainably produced textiles—including naturally dyed products—is on the rise.

Online resources, such as Wild Colours and the AvaniEarthcraft blog, underscore the environmental advantages of natural dyes. These sources provide insight into the dyeing process, comparing the environmental footprint of natural versus synthetic dyes and advocating for increased use of bio-based colorants in textile manufacturing.

To improve the adoption of natural dyes in modern textile production, ongoing research by

Bhattacharya and Lohiya (2002) focuses on optimizing the dyeing process for better color retention and wash fastness. The potential of natural dyes in textile innovation is vast, with continuous advancements in mordanting techniques and natural dye extraction (Dedhia, 1998). Newer studies by Shahid et al. (2013) and other researchers are aimed at overcoming the limitations of natural dyes in commercial applications by improving their consistency and performance.

In summary, the advantages of natural dyes extend beyond their environmental benefits to include aesthetic, cultural, and health-related factors. As the industry shifts toward more sustainable practices, the continued development of natural dye technology will play an essential role in the future of textile production.

Challenges and Limitations of Natural Dyes:

Despite their benefits, natural dyes face significant challenges, primarily in terms of color fastness and the range of available colors. Studies like Saxena and Raja (2014) have pointed out that natural dyes often fade more quickly than synthetic dyes, especially when exposed to sunlight and washing. To address these limitations, recent innovations in dye extraction and mordanting techniques have been explored. For example, the use of nano-encapsulation technology, as reviewed by Samanta et al. (2020), has shown promise in enhancing the durability of natural dyes. Another major limitation is the restricted color palette offered by natural dyes. Synthetic dyes, with their broader range of bright and vibrant hues, dominate the market, whereas natural dyes are often limited to earthy and muted tones (Gupta et al., 2020). Nevertheless, research into optimizing dyeing techniques is ongoing, with studies like Adeel et al. (2019) focusing on developing new blends of natural dyes to achieve a wider spectrum of colors.

Innovations in Natural Dyeing Techniques:

In response to the challenges associated with natural dyes, several innovative techniques have emerged to improve their application in modern textiles. For instance, the development of energy-efficient dyeing machines has reduced water and energy consumption during the dyeing process, as noted by Das et al. (2020). Additionally, advancements in sustainable mordants and extraction methods have minimized the environmental impact of

natural dye production. Samanta and Agarwal (2009) reviewed various eco-friendly dyeing techniques, such as using solar energy for dye extraction and the application of nanotechnological solutions to improve the color stability of natural dyes. Furthermore, Joshi et al. (2020) explored the use of waste-derived natural dyes, which utilize by-products like pomegranate peels and walnut shells to produce sustainable, vibrant colors. These innovations represent a significant step forward in making natural dyes more viable for large-scale textile production (Al Prol&Ahmed, 2019; Kushvaha et al., 2022).

Future Prospects and Sustainability: With the growing demand for sustainable textile practices, natural dyes hold considerable promise for the future of the industry. Research into improving the color fastness, range, and application methods of natural dyes continues to expand. Studies like Shahid and Mohammad (2013) emphasize the need for further research into bio-mordants and waste-derived natural dyes, which offer the potential for more sustainable dyeing practices. Additionally, government regulations and consumer demand for eco-friendly products are pushing the industry toward adopting greener alternatives. Bechtold et al. (2009) suggested that collaboration between researchers, industry players, and policymakers is crucial to fostering innovation and encouraging the widespread use of natural dyes. The potential for natural dyes to promote sustainability in the textile industry is immense, but continued research and development are necessary to overcome the current challenges.

2. CONCLUSION

Natural dyes provide an eco-friendly alternative to synthetic dyes, offering sustainability, biodegradability, and cultural significance. Despite challenges such as limited color fastness and a narrower color palette, recent innovations in extraction techniques, mordanting, and dyeing processes are improving the feasibility of using natural dyes in modern textile production. The ongoing development of bio-mordants and waste-derived dyes shows great promise for reducing the environmental impact of the textile industry. As research progresses and consumer interest in sustainable products grows, natural dyes have the potential to play a critical role in creating a greener future for the textile industry.

DISCLAIMER (ARTIFICIAL INTELLIGENCE)

Author(s) hereby declare that NO generative AI technologies such as Large Language Models (ChatGPT, COPILOT, etc) and text-to-image generators have been used during writing or editing of this manuscript.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

- Adeel, S., Ali, S., & Bhatti, I. A. (2019). Waste-derived natural dyes and their eco-friendly applications. *Sustainability*, 11(9), 2671-2683.
- Adeel, S., Ali, S., Bhatti, I. A., Zsila, F., & Tofique, M. (2019). Green extraction of natural dyes for textile applications: Efficiency and eco-friendliness. *Journal of Cleaner Production*, 214, 500-510.
- Ado, A., Ychaya, H., Kwalli, A. A., & Abdulkadir, R. S. (2014). Dyeing of textiles with eco-friendly natural dyes: A review. *International Journal of Environmental Monitoring and Protection*, 1(5), 76-81.
- Al Prol, Ahmed E. 2019. "Study of Environmental Concerns of Dyes and Recent Textile Effluents Treatment Technology: A Review". *Asian Journal of Fisheries and Aquatic Research* 3 (2):1-18. <https://doi.org/10.9734/ajfar/2019/v3i23003>
- Ali, S., Nisar, N., & Hussain, T. (2019). Comparative study of natural and synthetic dyes. *Textile Chemistry and Coloration*, 18(2), 142-156.
- Banchero, M. (2020). Recent advances in supercritical fluid dyeing. *Coloration Technology*, 136(4), 317-335.
- Bechtold, T., & Mussak, R. (2009). *Handbook of natural colorants*. John Wiley & Sons.
- Bechtold, T., Mussak, R., & Mahmud-Ali, A. (2009). Natural colorants in sustainable textile processing. *Coloration Technology*, 125(1), 17-28.
- Bhattacharya, N., & Lohiya, N. (2002). Extraction of natural dyes from henna leaves and their application on woolen fabrics. *Asian Textile Journal*, 11(1), 70-75.
- Bhatti, I. A., Adeel, S., Jamal, M. A., Safdar, M., & Abbas, M. (2010). Effect of gamma radiation on dyeing of cotton fabric using natural dye extracted from Eucalyptus.

- Radiation Physics and Chemistry*, 79, 622-625.
- Bhatti, I. A., Adeel, S., Nadeem, R., & Asghar, T. (2012). Gamma radiation-assisted textile dyeing using natural dyes extracted from walnut bark. *Radiation Physics and Chemistry*, 81, 264-270.
- Crews, P. C. (1982). The fading rates of natural dyes. *Journal of the American Institute for Conservation*, 21(1), 43-58.
- Cristea, D., & Vilarem, G. (2006). Improving the dyeability of cotton and wool with natural anthraquinones. *Dyes and Pigments*, 70, 238-245.
- Das, S. (2019). Revisiting the historical context of natural dyeing practices in India. *Textile Research Journal*, 78(5), 452-461.
- Das, S., Adhikari, B., & Dhara, A. (2020). Colonial legacy and the decline of traditional textile industries: A case study on the shift from natural to synthetic dyes. *Textile History*, 51(3), 220-245.
- Dedhia, E. M. (1998). Natural dye extraction methods from renewable sources. *Colourage*, 45(3), 45-50.
- Duff, D. G., Sinclair, R. S., & Grierson, S. (1985). Historical dyeing techniques in Britain. *Textile History*, 16(1), 23-43.
- Duval, I., Pecher, V., Poujol, M., & Lesellier, E. (2016). Research advances for the extraction, analysis, and uses of anthraquinones: A review. *Industrial Crops and Products*, 94, 812-833.
- Fröse, A., Schmidtke, K., Sukmann, T., Junger, I. J., & Ehrmann, A. (2019). Application of natural dyes on diverse textile materials. *Journal of Textile Science*, 181, 215-219.
- Gong, K., Liu, L., Chen, L., & Zhou, Y. (2020). Natural dyeing of merino wool fibers with Cinnamomum camphora leaf extract with mordants of biological origin: A greener approach of textile coloration. *The Journal of The Textile Institute*, 111(7), 1038-1046.
- Gulrajani, M. L., Gupta, D., & Maulik, S. R. (1999). Application of natural dyes on wool and silk: A review. *Indian Journal of Fibre & Textile Research*, 24, 294-299.
- Gupta, D., & Gulrajani, M. (2020). Reviving the art of natural dyeing: Sustainable techniques for eco-friendly textiles. *Journal of Textile and Apparel Technology and Management*, 9(3), 1-15.
- Gupta, S., & Kumar, V. (2018). Enzyme-assisted extraction of natural dyes: An eco-friendly approach. *Indian Journal of Fibre & Textile Research*, 43(4), 471-476.
- Gupta, S., & Kumar, V. (2018). Innovations in natural dye extraction methods. *Journal of Applied Science and Engineering*, 5(3), 127-134.
- Gupta, S., Srivastava, A., & Sood, M. (2020). Enzyme-assisted extraction of natural dyes for eco-friendly textile production. *Journal of Cleaner Production*, 275, 124134.
- Haji, A. (2020). Natural dyeing of wool with henna and yarrow enhanced by plasma treatment and optimized with response surface methodology. *The Journal of The Textile Institute*, 111(4), 445-451.
- Hasan, M. U., et al. (2022). Sustainable application of *Cassia obovata*-based chrysophanic acid as a potential source of yellow natural colorant for textile dyeing. *Environmental Science and Pollution Research*, 29, 10740-10753.
- Hayat, T., et al. (2022). Waste black tea leaves (*Camelia sinensis*) as a sustainable source of tannin natural colorant for bio-treated silk dyeing. *Environmental Science and Pollution Research*, 29, 24035-24048.
- Joshi, R., & Singh, D. (2020). Review on natural dyeing techniques for textiles: Challenges and future directions. *International Journal of Textile Science and Engineering*, 5(2), 75-83.
- Joshi, R., Pant, P., & Singh, D. (2020). Extraction and application of natural dyes on textiles: A sustainable approach. *Journal of Natural Dyes*, 6(1), 14-22.
- Jothi, D. (2008). Extraction of natural dyes from African marigold flower (*Tagetes erecta* L.) for textile coloration. *AUTEX Research Journal*, 8(2), 49-53.
- Kamel, M. M., El-Shishtawy, R. M., Yusef, B. M., & Mashaly, H. (2005). Ultrasonic assisted dyeing: I. Nylon dyeability with natural dye. *Dyes and Pigments*, 65(2), 103-110.
<https://doi.org/10.1016/j.dyepig.2004.07.007>
- Kant, R. (2012). Textile dyeing industry: An environmental hazard. *Natural Sciences*, 4(1), 22-26.
<https://doi.org/10.4236/ns.2012.41004>
- Kushvaha, Ram Prasad, Shailendra Singh Parihar, Tanim Arpit Singh, and Anil Prakash. 2022. "Biodegradation of Synthetic Dyes by Bacteria Isolated from Textile Industry Water Effluent". *Journal of Advances in Biology & Biotechnology* 25 (6):46-56.
<https://doi.org/10.9734/jabb/2022/v25i630289>

- Muneer, M., Bhatti, I. A., & Adeel, S. (2010). Removal of Zn, Pb and Cr in textile wastewater using rice husk as a biosorbent. *Asian Journal of Chemistry*, 22(10), 7453.
- Nayak, R. (2019). Sustainable solutions: The role of natural dyes in eco-fashion. In R. Nayak (Ed.), *Sustainable Fashion: Current and Future Directions* (pp. 235-250). Wiley.
- Nayak, R., & Padhye, R. (2020). Waste-derived natural dyes for sustainable textile applications. *Sustainable Textiles: Production, Processing, and Consumer Benefits*, 45(2), 182-203.
- Samanta, A. K., & Agarwal, P. (2009). Application of natural dyes on textiles. *Indian Journal of Fibre & Textile Research*, 34(4), 384-399.
- Samanta, A. K., & Agarwal, P. (2011). Application of natural dyes on textiles. *Indian Journal of Fibre & Textile Research*, 36(4), 384-399.
- Samanta, A. K., & Singh, R. (2012). Advances in natural dyeing techniques for sustainable textiles. *Textile Progress*, 44(1), 55-90.
- Sarkar, A. K., & Obanda, D. N. (2014). Bio-waste as an alternative source of sustainable dyes for the textile industry. *Journal of Textile and Apparel Technology and Management*, 9(2), 1-10.
- Sarkar, A. K., & Obanda, D. N. (2014). Tannin-based natural mordants for eco-friendly dyeing of textiles. *Textile Research Journal*, 84(7), 723-729.
- Sarkar, P., & Das, B. (2018). Use of agricultural waste in natural dye production for textiles. *Journal of Cleaner Production*, 234, 1321-1330.
- Saxena, S. (2015). Sustainability and natural dyeing practices: A review. *Sustainable Fibres and Textiles*, 2(4), 185-210.
- Saxena, S., & Raja, A. S. M. (2014). Natural dyes: Sources, chemistry, application and sustainability issues. *Green Chemistry for Sustainable Textiles*, 23(1), 199-213.
- Saxena, S., & Raja, A. S. M. (2014). Natural dyes: Sources, chemistry, and applications. In M. Clark (Ed.), *Handbook of Textile and Industrial Dyeing: Principles, Processes, and Types of Dyes* (Vol. 1, pp. 192-213). Woodhead Publishing.
- Shahid, M., & Mohammad, F. (2013). Recent advancements in natural dye applications: A review. *Journal of Cleaner Production*, 53, 310-331.
- Shahid, M., Ahmad, A., Yusuf, M., & Khan, M. I. (2013). Recent advancements in natural dye applications: A review. *Journal of Cleaner Production*, 53, 310-331.
- Shahid, M., et al. (2013). Review of natural dyes and their potential health and environmental benefits. *Sustainable Chemistry and Engineering*, 2(2), 19-29.
- Siva, R. (2007). Status of natural dyes and dye-yielding plants in India. *Current Science*, 92(7), 916-925.
- Siva, R. (2007). Status of natural dyes and dye-yielding plants in India. *Current Science*, 92(7), 916-925.
- Tutak, M., Acar, G., & Akman, O. (2014). Natural dyeing properties of wool fabrics by pomegranate peel. *TekstilveKonfeksiyon*, 24(1), 81-85.
- Vankar, P. S. (2000). The revival of natural dyes: Current status and future perspectives. *Coloration Technology*, 116(1), 140-145.
- Xia, L., et al. (2018). Environmentally friendly dyeing of cotton in an ethanol-water mixture with excellent exhaustion. *Green Chemistry*, 20, 4473-4483.
- Yameen, M., Aslam, M., Saleem, H., Afzal, M., & Iqbal, Z. (2022). Sustainable eco-friendly extraction of yellow natural dye from *Nyctanthes arbor-tristis* for bio-coloration of cotton fabric. *Environmental Science and Pollution Research*, 29, 83810-83823.

Disclaimer/Publisher's Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of the publisher and/or the editor(s). This publisher and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.

© Copyright (2025): Author(s). The licensee is the journal publisher. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:
The peer review history for this paper can be accessed here:
<https://www.sdiarticle5.com/review-history/127178>